

SPECIALI

SPECIALS


COTTOSTONE



Tecnostone



Cocciopesto



Palladiana

SCHEDA TECNICA	NORME	VALORI CONFORMI A EN-NORM	VALORI MANETTI
Densità apparente	EN 14617-1	–	Mv = 2192 kg/m ³
Assorbimento d'acqua	EN 14617-1	–	C = 0,5%
Resistenza a flessione	EN 14617-2	–	25,0 < F3 < 40
Dilatazione termica lineare	EN 14617-11	–	$\alpha = 17-26 \times 10^{-6}$
Resistenza allo scivolamento	DIN EN 16165 Annex B	Prova su piano inclinato	R10 Rocplan 2.0 / R9 Grain 2.0